

## OSM/LUM DECISION SHEET (DSH)

Standard(s) (incl. year)	Subclause(s):	Tracking No.	Year
EN 60598-1:2015/A1:2018	13.2.1	DSH 0929A	2019
<b>Category:</b>			
LITE			
Subject:	Key words:	Developed by	Approved at
Temperature for ball pressure test	<ul style="list-style-type: none"> <li>- Temperature</li> <li>- Hottest point</li> <li>- Inner surface</li> </ul>	OSM/LUM-ETF5	2019 ETICS Plenary Meeting

### Question

External parts of insulating material providing protection against electric shock shall be subjected to ball pressure test according to clause 13.2.1 of EN 60598-1. The temperature is measured during the heating test in normal operation. Where is this temperature to be measured?

### Decision

The temperature in question shall be measured at hottest point found on the relevant part (normally on the inner surface of an enclosure).

### Explanatory notes

---